



# PILES UNDERWATER INSPECTION


Rev. 1

Date: 07/04/2023

INSPECTION DATE: 4-jul-23

## 1. PILE DATA

LOCATION:



NOMENCLATURA:

P - 04

PILE DIAMETER:

Underwater inspection was carried out to check the conditions of the pile both on the surface and under water.

## PHOTOGRAPHIC RECORD



Image 1: Pile - nomenclature P-04



Image 2: Pile P-04 Below tide level covered largely by organisms.



Image 3: Pile P-04 covered by marine organisms and corrosion on patches.



Image 4: Pile P-04 metal expose with presence of corrosion and porosity.

Severe Damage					Loss of cross - sectional area, or evaluate material			
STRUCTURE STATUS / LEVEL	STEEL COATING	CONCRETE	WOOD	COMPOSITE	STEEL COATING	CONCRETE	WOOD	COMPOSITE
I		N/A	N/A	N/A	N/A	N/A	N/A	N/A
II	X	N/A	N/A	N/A	N/A	N/A	N/A	N/A
III		N/A	N/A	N/A	N/A	N/A	N/A	N/A
IV		N/A	N/A	N/A	N/A	N/A	N/A	N/A
Observations: There is evidence of porosity, and corrosion on the steel coating surface.					Observations: there is no evidence of loss material.			

Surface defects normally obscured by marine growth				
STRUCTURE STATUS / LEVEL	STEEL	CONCRETE	WOOD	COMPOSITE
I		N/A	N/A	N/A
II		N/A	N/A	N/A
III		N/A	N/A	N/A
IV	X	N/A	N/A	N/A
Observations: The structure is completely covered by marine growth				

Routine Underwater Conditions Assessment Rating	
Rating	Description
6 Good	6. No visible damage, or only minor damage is noted. Structural elements may show very minor deterioration, but no overstressing is observed. No repairs are required.
5 Satisfactory	
4 Fair	
3 Poor	

2	Serious	
1	Critical	

**Recommended Minimum scope of routine inspections - Inspection sample size and method (s)**

0

Material	Level	Sample Size (100%)	method
Concrete	i	100	Visual or tactile presence of corrosion on steel coated
Piles	ii	10	
	iii	5	
Large elements2	i	100	
	ii	Every 100 ft	
	iii	Every 200 ft	
Steel	i	100	
Piles	ii	10	
	iii	0	
Large Elements2	i	100	
	ii	Every 100 ft	
	iii	0	

ELABORATED BY ASTURIAS INGENIERIA	DIVING SUPERVISOR	VoBo	OBSERVATIONS
Lead Diver: Piter Cuero	Juan D. Zapata Chacon	Camilo A. Chacon	No serious damages or cracking were found both on the surface and below tide levels.